



**DEFENSE LOGISTICS AGENCY  
LAND AND MARITIME  
P.O. BOX 3990  
COLUMBUS, OHIO 43218-3990**

6 June 2016

**MEMORANDUM FOR MILITARY/INDUSTRY DISTRIBUTION**

**SUBJECT:** Initial Draft(s) of: MIL-PRF-49291/10B W/Amendment 1, MIL-PRF-49291/11B W/Amendment 2 and MIL-PRF-49291/12B W/Amendment 1  
Project Number(s): 6010-2016-002, 6010-2016-003, and 6010-2016-004, respectively.

The initial draft(s) for these subject document(s), are now available for viewing and downloading from the DLA Land and Maritime-VA Web site:

<http://www.landandmaritime.dla.mil/programs/milspec/>

These QPL documents are being amended to add modify the temperature life aging requirements to assist in the qualification process. Concurrence or comments are required at this Center within 30 days from the date of this letter. Late comments will be held for the next coordination of the document. Comments from military departments must be identified as either "Essential" or "Suggested". Essential comments must be justified with supporting data. Military review activities should forward comments to their custodians of this office, as applicable, in sufficient time to allow for consolidating the department reply. Lack of response to this draft will be construed as concurrence.

If these document(s) are of interest to you, please provide your comments or suggested changes. The point of contact for this document is Ms. McWilliams, phone number 614-692-0571, facsimile transmission, 614-692-6939, e-mail [Mary.McWilliams@dla.mil](mailto:Mary.McWilliams@dla.mil), or may be mailed via the US Postal Service to DLA LAND AND MARITIME, ATTN: VAT (Attention: Mary McWilliams), P.O. Box 3990, Columbus, OH 43218-3990.

Sincerely,

/signed/

**MICHAEL A. RADECKI**  
Chief,  
Electronic Components Branch

cc:  
[DSCC.Standardization@dla.mil](mailto:DSCC.Standardization@dla.mil)

NOTE: This draft, dated 7 JUNE 2016, prepared by DLA-CC, has not been approved and is subject to modification, DO NOT USE PRIOR TO APPROVAL. (Project 6010-2016-004)

METRIC

MIL-PRF-49291/12B  
w/Amendment 1  
Draft  
SUPERSEDING  
MIL-PRF-49291/12B  
10 July 2013


PERFORMANCE SPECIFICATION SHEET

FIBER, OPTICAL, TYPE I, CLASS I, SIZE III, COMPOSITION A, WAVELENGTH B, RADIATION RESISTANT, ENHANCED PERFORMANCE CHARACTERISTICS/AIRCRAFT APPLICATIONS (METRIC)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-49291.

For legacy use only. For new platforms using multimode fiber, the Joint Fiber Optic Working Group (JFOWG) has imposed standardization with MIL-PRF-85045/31 fiber optic cable containing MIL-PRF-49291/10 multimode optical fiber. This specification sheet applies to existing platforms (ones in which the contract has been awarded) where the fiber optic portion of the network uses 50/125 micron fiber size.




| PIN                             | Dimensions |         |                                   |
|---------------------------------|------------|---------|-----------------------------------|
|                                 | A (µm)     | B (µm)  | C (µm)                            |
| M49291/12 -01<br>M49291/12 -01A | 50 ± 2.5   | 125 ± 1 | 500 ± 25<br><u>1/</u> , <u>2/</u> |
| M49291/12 -02<br>M49291/12-02A  | 50 ± 2.5   | 125 ± 1 | 245 ± 7<br><u>2/</u>              |

FIGURE 1. Dimensions and configuration of optical fiber construction.

- 1/ Coating shall conform to C diameter except a diameter of 450 ± 25 microns (µm) is permitted but less preferred for purposes of standardization.
- 2/ Integrated fiber and cable manufacturing process may exceed this diameter. When this condition occurs, then this configuration shall conform to cabling specification in addition to this specification sheet.

MIL-PRF-49291/12B  
W/ Amendment 1  
DRAFT DATED 7 JUNE 2016



| Circle (solid) | Diameter ( $\mu\text{m}$ ) |
|----------------|----------------------------|
| Inner          | 47.5                       |
| Second         | 52.5                       |
| Third          | 124.0                      |
| Fourth         | 126.0                      |

FIGURE 2. Tolerance fields.

Part or identifying number (PIN). (See figure 1 and table II):

- M49291/12-01
- M49291/12-01A
- M49291/12-02
- M49291/12-02A

**DIMENSIONS AND CONFIGURATION:**

Diameter: See figures 1 and 2. (Diameter requirements are based on selecting fibers with end-point tolerances of  $125 \pm 1 \mu\text{m}$  from production with a  $125 \pm 2 \mu\text{m}$  tolerance.)

Ovality:

- Core:  $\leq 5$  percent.
- Cladding:  $\leq 1$  percent.

Offset:

- Core-to-cladding:  $\leq 2 \mu\text{m}$ .

MIL-PRF-49291/12B  
W/ Amendment 1  
DRAFT DATED 7 JUNE 2016

Fiber-to-coating:

Coating-cladding concentricity error:  $\leq 10.5 \mu\text{m}$ .

Overall coating concentricity ratio (OCCR or Coating Noncircularity):  $\geq 0.75$  for a 250  $\mu\text{m}$  diameter coating,  $\geq 0.65$  for a 500  $\mu\text{m}$  diameter coating.

Fiber curl: Not applicable.

Splices within the optical fiber: Splices within the optical fiber are not allowed.

Tensile proof (fiber proof test): 1.38 GPa (200 kpsi).

Fiber mass/unit length: 0.1 kg/km maximum for 250  $\mu\text{m}$  coating, 0.3 kg/km maximum for 500  $\mu\text{m}$  coating.

Optical parameters:

Change in optical transmittance: Measurements to be made at  $850 \pm 20 \text{ nm}$ . Multiple fibers may not be concatenated during the measurement of change in optical transmittance. The center wavelength and light launch conditions for the specified fiber size and temperature range shall be as specified in [MIL-STD-1678-2](#).

Insertion loss: The insertion loss measurements shall be performed per [TIA-455-34](#) with the exception for adhering strictly to the setup and test procedure specified in Measurement 2101 of [MIL-STD-1678-2](#). Multiple fibers may not be concatenated during the measurement of change in optical transmittance or optical discontinuity. The center wavelength and light launch conditions for the specified fiber size and temperature range shall be as specified in [MIL-STD-1678-2](#).

Maximum attenuation rate: Spectral attenuation shall be performed at a sufficient number of wavelengths to cover the applicable optical transmission windows and sources for attenuation. Sufficient coverage includes the optical transmission windows (850 nm, 1,300 nm), ultraviolet absorption band (600 to 870 nm), Rayleigh scattering losses (800 to 1,200 nm), OH impurity absorption peaks (945, 1,249 and 1,383 nm). Use of a source and power meter to perform this measurement is not acceptable. Attenuation rate for wavelengths of operation shall not exceed the maximum values listed below. Attenuation rate for wavelengths of operation shall not exceed 3.0 dB/km at  $850 \pm 20 \text{ nm}$  and 0.8 dB/km at  $1,300 \pm 20 \text{ nm}$ . Maximum attenuation over the wavelength range from 800 to 1,600 nm shall be less than 3.5 dB/km.

Numerical aperture:  $0.200 \pm 0.015$  at  $850 \pm 25 \text{ nm}$ .

Overfill bandwidth:  $\geq 1,500 \text{ MHz-km}$  at  $850 \pm 20 \text{ nm}$  and  $\geq 500 \text{ MHz-km}$  at  $1,300 \pm 20 \text{ nm}$ .

EMB<sub>c</sub> bandwidth:  $\geq 1,500 \text{ MHz-km}$  at  $850 \pm 20 \text{ nm}$  when measured in accordance with TIA-455-220 including the use of the weightings found in annex D of this TIA standard.

Chromatic dispersion: Zero dispersion wavelength shall be  $1,313 \pm 18 \text{ nm}$ . The value of the slope at the zero dispersion wavelength shall be not greater than  $0.11 \text{ ps/nm}^2\text{-km}$  for a zero dispersion wavelength between 1,295 nm to 1,330 nm.

Transient attenuation:  $\leq 1.5 \text{ dB}$  at 1300 nm.

MIL-PRF-49291/12B  
W/ Amendment 1  
DRAFT DATED 7 JUNE 2016

Attenuation uniformity: Applicable except the attenuation uniformity shall be performed at 850 nm and 1,300 nm. There shall be no discontinuities in attenuation along the length greater than 0.2 dB.

Macrobend attenuation: Applicable. Test shall be performed in accordance with 4.7.2.4 and measured in accordance with TIA-455-62, Method B, with optical power measurements obtained for each row of parameters in table I.

TABLE I. Macrobend attenuation test parameters.

| Mandrel diameter<br>mm (Inch) | Number of<br>turns around<br>mandrel | Measurement<br>wavelength<br>(nm) | Macrobend<br>attenuation<br>(dB) |
|-------------------------------|--------------------------------------|-----------------------------------|----------------------------------|
| 30 ± 1<br>(1.2 ± .04)         | 2                                    | 1,300 ± 20                        | 1.5                              |
| 30 ± 1<br>(1.2 ± .04)         | 2                                    | 850 ± 25                          | 1.5                              |
| 20 ± 1<br>(.79 ± .04)         | 1                                    | 1,300 ± 20                        | 2.5                              |
| 20 ± 1<br>(.79 ± .04)         | 1                                    | 850 ± 25                          | 2.5                              |
| 15 ± .5<br>(.59 ± .02)        | 1                                    | 1,300 ± 20                        | 3.5                              |
| 15 ± .5<br>(.59 ± .02)        | 1                                    | 850 ± 25                          | 3.5                              |

Polarization mode dispersion: Not applicable.

ENVIRONMENTAL:

Temperature range: See table II.

TABLE II. Temperature range.

| PIN                                      | Operating<br>°C (° F)       | Nonoperating<br>°C (° F)    | Storage<br>°C (° F)        |
|--|-----------------------------|-----------------------------|----------------------------|
| M49291/12-01<br>M49291/12-02 <u>1/</u>   | -55 to +165<br>(-67 to 329) | -40 to + 85<br>(-40 to 185) | -40 to +85<br>(-40 to 185) |
| M49291/12-01A<br>M49291/12-02A <u>2/</u> | -46 to +85<br>(-51 to 185)  | -55 to +85<br>(-67 to 185)  | -55 to +85<br>(-67 to 185) |

1/ Temperature ranges in row 2 conform to those specified for other MIL-SPEC fiber optic cabling components for aircraft applications.

2/ Temperature ranges in row 3 conform to those specified for other MIL-SPEC fiber optic cabling components for standard applications (such as the telecommunication industry).

Fluid immersion aging: Not applicable.

Mechanical strippability: Applicable except, in addition, each individual optical fiber shall comply with the below requirements and test method for diameter in addition to the 3.5.3 (of MIL-PRF-49291)

MIL-PRF-49291/12B  
W/ Amendment 1  
DRAFT DATED 7 JUNE 2016

residue coating and fiber damage. Also, guidance is provided for determining the strip force using the method specified in TIA-455-178.

Strip force determination. When the mechanical strippability is performed to TIA-455-178, the test apparatus (such as a tensile test machine) parameters should be set up for adequate mechanical strippability to measure the strip force. Stripping speed (rate) and duration may be determined and set to achieve the strip force over an approximate length. Guidance for starting values to determine stripping speed and time can be obtained in 5.2 of TIA-455-178 for stripping rate and 4.1 of TIA-455-178 for length and iterate as needed. A plot of strip force versus time (or strip length) for each strip performed is preferred. Ten tests for strip force shall be performed on each length of optical fiber length cut from each spool.

Diameter requirement. Requirement that the stripped optical fiber complies with diameter B in figure 1 shall be verified by successful insertion and removal of each optical fiber stripped end into a ring gauge/die/ferrule with a hole diameter of  $125 +1/-0$  micron. It is in the interest of the implementer to choose a gauge closer to 126 micron than 125 microns.

Coating adherence. Requirement for coating adherence shall be verified by the performance of a fiber pullout test. The end of each stripped length of optical fiber shall be terminated onto the end of a MIL-PRF-29504 terminus (or other suitable fiber optic connector if approved by the qualifying activity prior to test sample fabrication). Fabrication shall be performed as specified in Requirement 4101, Requirement 4102 or Requirement 4103 of MIL-STD-1678-4, as applicable. The fiber pull out force shall be tested by applying a 14.0 N (3.1 pounds) axial tensile load between the optical fiber and the terminus for a minimum duration of one minute. At the completion of the test, the optical fiber shall be visually examined and length measured to verify that no fiber pull out occurred. One optical fiber length from each spool used for the Group 2 mechanical strippability test shall be tested for cable pullout force. The test entity is given the latitude to affix the terminus in a clamp, corrector or other fixture of their choice and the method of applying the force.

Splice compatibility. Six 10 meter (32.8 feet) lengths of optical fiber conforming to the requirements of this specification sheet shall be spliced, (using either a fusion splicer or mechanically splice) and connectorized (using MIL-PRF-29504/4 and MIL-PRF-29504/5 termini) to optical fiber conforming to MIL-PRF-49291/7. Three sample lengths are to be used for each splice or connector. Start by obtaining the baseline measurement of the uncut, 10 meter length, of optical fiber. Cut the optical fiber in half (i.e., at 5 m from the end) and either terminate each fiber (at the 5 m cut) with MIL-PRF-29504/4 and /5 termini or splice a MIL-PRF-49291/7 optical fiber between the cut ends. An insertion loss measurement shall be performed in accordance with Method A2 (i.e., a restricted launch condition) of TIA/EIA-455-34. The insertion loss shall not exceed 0.2 dB per splice and 0.5 dB per connector mated pair when performed at a wavelength of 1,310 nm. Repeat this sequence until three 10 meter lengths is terminated with termini in the middle and three 10 meter lengths are spliced with MIL-PRF-49291/7 optical fiber in the middle.

Dynamic tensile strength: Applicable except that 30 test samples from each spool shall be tested with no humidity (i.e., under specified room conditions) with the calculations performed for the 30 samples tested. Testing shall be performed with the gage length of 500 mm (19.7 inch), test speed (strain rate) of 2.5 mm/min (0.098 in/min) and speed to pre-load of 1.25 mm/min (0.049 in/min).

Fungus: Applicable.

Thermal shock:

Applicable as specified for M49291/12-01A and M49291/12-02A (in accordance with 4.8.1 of MIL-

MIL-PRF-49291/12B  
W/ Amendment 1  
DRAFT DATED 7 JUNE 2016

PRF-49291).

Applicable for M49291/12-01 and M49291/12-02, except that the temperatures of  $-55^{\circ}\text{C} +0/-5^{\circ}\text{C}$  ( $-67^{\circ}\text{F} +0/-8^{\circ}\text{F}$ ) and  $165^{\circ}\text{C} +5/-0^{\circ}\text{C}$  ( $329^{\circ}\text{F} +8/-0^{\circ}\text{F}$ ) shall be used for the low and high soak temperatures, respectively. Test shall be performed in accordance with TIA-455-71, schedule C-0 (5 cycles). The change in optical transmittance shall be measured during (towards the end of each soak temperature) and after the test.

Storage temperature: Applicable.

Temperature cycling:

Applicable as specified for M49291/12-01A and M49291/12-02A (in accordance with 4.8.3 of MIL-PRF-49291).

Applicable for M49291/12-01 and M49291/12-02 except for the optical fiber with a  $-55^{\circ}\text{C}$  to  $165^{\circ}\text{C}$  ( $-67^{\circ}\text{F}$  to  $329^{\circ}\text{F}$ ) temperature range, perform the following in lieu of the specified temperature cycling test. Optical fiber shall be tested in accordance with TIA-455-3 using the setup and procedure specified in measurement 3301 of MIL-STD-1678-3 with the temperature profile in table 3301-II. The change in optical transmittance shall be measured during and after the test. At a minimum for the "during test" measurements, an optical transmittance measurement shall be performed towards the end of each soak period (maintain step) after every 50 cycles. A post test visual examination of the test specimens shall reveal no surface impairment or any damage detrimental to the operation of the test specimens. Test fixtures, if used, must be of minimum mass and approved by the qualifying activity. No other mass (item that causes significant thermal lag) shall be added inside the chamber.

Temperature life (life aging):

Applicable as specified for M49291/12-01A and M49291/12-02A (in accordance with 4.8.4 of MIL-PRF-49291).

Applicable for M49291/12-01 and M49291/12-02, except that the high exposure temperature shall be  $165^{\circ}\text{C} +5/-0^{\circ}\text{C}$  ( $329^{\circ}\text{F} +8/-0^{\circ}\text{F}$ ). Test samples shall be tested in accordance with TIA/EIA-455-4 for the duration of 1,000 hours at the high exposure temperature. The change in optical transmittance shall be measured after the test. An optical transmittance measurement is requested to be taken daily for informational purposes only. The optical fiber shall be visually examined after the test to the extent feasible. Optical fiber shall not be damaged, and there shall be no distortion, cracking of coating, or other damage detrimental to the operation of the optical fiber. The requirement for the change in optical transmittance shall be met after the test. Performance of a cable/fiber retention test is not required as part of the final inspection for this test.

Nuclear radiation resistance: Nuclear radiation resistance requirements and test conditions shall be as shown below and in table III and table IV:

Light launch conditions: In accordance with TIA-455-78.

Wavelength:  $1,300 \pm 25$  nm.

Source type: LED with FWHM spectral width  $\leq 160$  nm.

TABLE III. Steady state gamma radiation test conditions.

| Test temperature $^{\circ}\text{C}$ | Dose rate | Total dose (rad Si) <u>1/</u> |
|-------------------------------------|-----------|-------------------------------|
|-------------------------------------|-----------|-------------------------------|

MIL-PRF-49291/12B  
W/ Amendment 1  
DRAFT DATED 7 JUNE 2016

|                             |                            |            |
|-----------------------------|----------------------------|------------|
| -28 ± 2<br>25 ± 2<br>85 ± 2 | 50 +0, -20<br>rad (Si)/sec | Classified |
|-----------------------------|----------------------------|------------|

1/ Some nuclear radiation resistance characteristics of this optical fiber are classified and shall be obtained from the qualifying activity. Application to receive these requirements must be made through the Department of the Navy, Naval Surface Warfare Center, Dahlgren Division, ATTN: Code W13, 17214 Avenue B Suite 125, Dahlgren, VA 22448-5147. Information concerning security clearance classification and "need to know" must be detailed in the request.

TABLE IV. Steady state gamma radiation test requirements.

| Maximum induced attenuation (dB/km) | Attenuation at specified recovery time (dB/km)                                   | Specified recovery time (sec) |
|-------------------------------------|--|-------------------------------|
| ≤ 50 <u>1/</u>                      | ≤ 15 at -28° C (-18°F) <u>1/</u><br>≤ 5 at 25° C (-18°F)<br>≤ 5 at 85° C (185°F) | 1,000                         |

1/ The radiation induced loss for a given threat. The total dose associate with the threat is classified and not necessarily equal to the test total dose.

CONFORMANCE:

Test samples for qualification: Reels of optical fiber produced for initial qualification shall be from at least two different preforms (see 4.5.1 of MIL-PRF-49291).

Qualification: Qualification shall consist of performing testing specified in table V.

TABLE V. Qualification inspections.

| Test performed                       | Initial qualification |
|--------------------------------------|-----------------------|
| Initial uncoiling preparation        |                       |
| Group 1 (3 spools-2 km ea) <u>1/</u> |                       |
| Visual and mechanical                | X                     |
| OTDR tests:                          |                       |
| Fiber length                         | X                     |
| Attenuation uniformity               | X                     |
| Parameter tests:                     |                       |
| Attenuation rate                     | X                     |
| Numerical aperture (MM only)         | X                     |
| Core diameter (MM only)              | X                     |

See footnotes at end of table.

MIL-PRF-49291/12B  
W/ Amendment 1  
DRAFT DATED 7 JUNE 2016

TABLE V. Qualification inspections - Continued.

| Test performed  | Initial qualification |
|---|-----------------------|
| Cutoff wavelength(SM only)  |                       |
| Mode field diameter (SM only)   |                       |
| Transient attenuation (MM only)   | X                     |
| Macrobend attenuation   | X                     |
| Bandwidth-overfill (MM only)  | X                     |
| Bandwidth-RML/EMBc (MM only)  | X                     |
| Chromatic dispersion  | X                     |
| Polarization mode dispersion (SM only)  |                       |
| Fiber curl (SM only)  |                       |
| Mass/unit length  | X                     |
| Geometry tests:   |                       |
| End view:   |                       |
| Core ovality (MM only)  | X                     |
| Cladding diameter   | X                     |
| Cladding ovality  | X                     |
| Core to cladding offset   | X                     |
| Side view:  |                       |
| Coating diameter  | X                     |
| Coating-cladding concentricity error  | X                     |
| Overall coating concentricity ratio   | X                     |
| Group 2 (samples off 3 spools) <u>1/</u>                                      |                       |
| Tensile proof   | X                     |
| Mechanical strippability  | X                     |
| Dynamic tensile strength  | X                     |
| Splice compatibility  | X                     |
| Coating adherence   | X                     |
| Group 3 (same 3 spools-2km ea <u>1/</u> , <u>2/</u> , <u>5/</u> , <u>6/</u> ) |                       |
| Thermal shock <u>4/</u>   | X                     |
| Storage temperature <u>4/</u>   | X                     |
| Temperature humidity cycling <u>4/</u>  | X                     |
| Mechanical strippability (post TH cycling)                                    | X                     |
| Temperature cycling <u>4/</u>   | X                     |
| Temperature life (life aging) <u>3/</u> , <u>7/</u>                           | X                     |
| Mechanical strippability (post Temp life)                                     | X                     |
| Group 4(samples off 3 spools)   |                       |
| Nuclear radiation resistance <u>4/</u>  | X                     |

MIL-PRF-49291/12B  
W/ Amendment 1  
DRAFT DATED 7 JUNE 2016

Fungus resistance

X

NOTES:

- 1/ See table I in basic specification (MIL-PRF-49291) for specimen lengths.
- 2/ OOT = Change in optical transmittance. Perform in accordance with TIA-455-20 for transmitted power adhering strictly to the setup and test procedure specified in measurement 2102 of MIL-STD-1678-2.
- 3/ Perform OOT after the test only.
- 4/ Perform OOT both during and after the test.
- 5/ Sample lengths: Recommend to prepare before group 1. For mechanical strippability, place in pans and remove from chamber after specified environmental test.
  - Mechanical strippability: each spool, 2 samples, 91.4 cm (3 ft) long.
  - Mechanical strippability-post temp/humidity: each spool, 2 samples, 91.4 cm (3 ft) long.
  - Mechanical strippability-post life aging: each spool, 2 samples, 91.4 cm (3 ft) long.
  - Dynamic tensile strength: each spool, 30 samples, 198.1 cm (6.5 ft) long (no humidity).
  - Nuclear radiation resistance: each spool, 1 sample, 200 meters (165.1 ft) long on spool.
  - Fungus resistance: each spool, 1 sample, 30.5 cm (1 ft) long.
- 6/ Prepare in loose coils and place in pans. Recommend to terminate with single ferrule connectors (such as ST connectors) on the fiber ends (for attachment to test instrumentation optical ports – to obtain more stabilized measurements).
- 7/ Measurements requested daily for informational purposes.

In group A testing length may be measured using mechanical methods.

In group C testing the mechanical strippability test may be omitted if the optical fiber coatings have not changed from when the mechanical strippability test was last performed. The manufacturer shall provide a certificate of compliance for mechanical strippability in the group C test report.

Qualification by similarity:

Change in glass:

Manufacturers who are qualified under this specification sheet and whose optical fiber with a change in the glass (composition, profile, etc.) passes the tests specified in table VI as specified herein are qualified under this specification sheet for the optical fiber with changed glass.

MIL-PRF-49291/12B  
W/ Amendment 1  
DRAFT DATED 7 JUNE 2016  
TABLE VI. Qualification by similarity (change in glass).

|                                 |
|---------------------------------|
| Visual and mechanical           |
| Fiber length                    |
| Attenuation uniformity          |
| Attenuation rate                |
| Numerical aperture (MM only)    |
| Core diameter (MM only)         |
| Cutoff wavelength (SM only)     |
| Mode field diameter (SM only),  |
| Transient attenuation (MM only) |
| Macrobend attenuation           |
| Bandwidth (MM only)             |
| Chromatic dispersion            |
| Temperature cycling             |
| Nuclear radiation resistance    |

Change in coating:

Manufacturers who are qualified under this specification sheet and whose optical fiber with a change in the coating (composition, thickness, etc.) passes the tests specified in table VII as specified herein are qualified under this specification sheet for the optical fiber with changed coating.

TABLE VII. Qualification by similarity (change in coating).

|                                     |
|-------------------------------------|
| Visual and mechanical               |
| Fiber length                        |
| Attenuation rate                    |
| Transient attenuation (MM only)     |
| Macrobend attenuation               |
| Coating diameter                    |
| Overall coating concentricity ratio |
| Mechanical strippability            |
| Dynamic tensile strength            |
| Thermal shock,                      |
| Storage temperature,                |
| Temperature humidity cycling,       |
| Temperature cycling,                |
| Temperature life (life aging)       |
| Fungus resistance                   |

MIL-PRF-49291/12B  
W/ Amendment 1  
DRAFT DATED 7 JUNE 2016

Reference documents: In addition to MIL-PRF-49291, this document references the following:

|                  |                  |                |
|------------------|------------------|----------------|
| MIL-STD-1678-2   | MIL-PRF-85045/31 | TIA-455-62     |
| MIL-PRF-29504    | TIA-455-3        | TIA-455-71     |
| MIL-PRF-29504/4  | TIA/EIA-455-4    | TIA-455-78     |
| MIL-PRF-29504/5  | TIA-455-20       | TIA-455-220    |
| MIL-PRF-49291/1  | TIA/EIA-455-34   | MIL-STD-1678-3 |
| MIL-PRF-49291/10 |                  |                |

Changes from previous issue: The margins of this specification are marked with vertical lines to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - CR  
Navy - AS  
Air Force – 85  
DLA – CC  
NASA - NA

Preparing activity:

DLA - CC

(Project 6010-2016-004)

Review activities:

Navy - SH  
Air Force – 02, 13, 19, 33, 93, 99  
DIA - DI

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at <https://assist.dla.mil>.